

Royal Stone |



*Inspired By Nature,
Made Possible By...*

CANCOS
TILE AND STONE

PORCELAIN STONEWARE



DOM ROCO 24



| 24 x 24 |

DOM ROCO 1224



| 12 x 24 |



DOM ROCO 12



| 12 x 12 |

DOM ROCO BN314



bullnose | 3 x 14 |

DOM ROCO HEX10



| 10 x 10 |
hexagon

DOM ROCO 314



| 3 x 14 |

DOM ROCO MOS22



12x12 sheet

mosaic | 2 x 2 |

PORCELAIN STONEWARE



DOM ROHA 24



| 24 x 24 |

DOM ROHA 1224



| 12 x 24 |

Havana



DOM ROHA 12



| 12 x 12 |

DOM ROHA BN314



bullnose

| 3 x 14 |

DOM ROHA HEX10



| 10 x 10 |

hexagon

DOM ROHA 314



| 3 x 14 |

DOM ROHA MOS22



12x12 sheet

mosaic

| 2 x 2 |

PORCELAIN STONEWARE



DOM ROLU 24



| 24 x 24 |

DOM ROLU 1224



| 12 x 24 |



DOM ROLU 12



| 12 x 12 |

DOM ROLU BN314




bullnose | 3 x 14 |

DOM ROLU HEX10



| 10 x 10 |
hexagon

DOM ROLU 314



| 3 x 14 |

DOM ROLU MOS22



12x12 sheet

mosaic | 2 x 2 |

PORCELAIN STONWARE



DOM ROSI 24



| 24 x 24 |

DOM ROSI 1224



| 12 x 24 |



DOM ROSI 12



| 12 x 12 |

DOM ROSI BN314



bullnose

| 3 x 14 |

DOM ROSI HEX10



| 10 x 10 |

hexagon

DOM ROSI 314



| 3 x 14 |

DOM ROSI MOS22



12x12 sheet

mosaic

| 2 x 2 |





HAVANA

Suggested Applications

floor wall residential light commercial heavy commercial exterior pools

Installation Suggestions

joint size modular setting plank installation edge: straight rustic rectified

finish: matte polished structured honed semi-polished other

Porcelain Type

through-body color-bodied glazed unglazed double-loaded other

Shade Variation

V1 Uniform Appearance V2 Slight Variation V3 Moderate Variation V4 Substantial Variation

thickness: 10 mm inches

Slip Resistance

Coefficient of Friction

	WET		DRY	
	standard*	result	standard*	result
accessible routes	.6		.6	
ramps	.8		.8	

Values: 0-0.50, 0.50-0.60, >0.60
 Tile Classification: Questionable, Conditionally Slip Resistant, Slip Resistant

DIN 51130: R9* 3-10°, R10 10-19°, R11 19-27°, R12 27-35°, R13 >35°

DIN 51097 Class: A, B, C

Typical applications: Barefoot, but mainly dry aisles and walkways, dry changing areas; Shower rooms, pool surrounds, wet changing areas, disinfectant spray areas (plus all Class A areas); Areas constantly under water, e.g. steps into pools, foot baths, included pool surrounds, jacuzzis (plus all Class A&B areas)

Critical angle: ≥12°, ≥18°, ≥24°

*Industry Standard/ADA Requirements

ASTM C-1028
DIN 51097/51130

Scratch Resistance

Mineral

- Talc (Talc)
- Gypsum (Fingernail)
- Calcite (Penny)
- Flourite (Some Marbles)
- Apatite (Knife Blade)
- Microline (Glass, Glazed Tile)
- Quartz (Unglazed Porcelain)
- Topaz (Granite)
- Corundum (Ruby)
- Diamond (Diamond)

Industry standard ≤175mm²

MOH'S SCALE **8**
UNI EN ISO 10545.6

Wear Resistance

PEI RATING UNI EN ISO 10545.7

Class 1: Walls only
 Class 2: Resid. floors w/minimal abrasive traffic.
 Class 3: Resid. interiors normal use and foot traffic.
 Class 4: Light-medium commercial applications.
 Class 5: Commercial applications.

Stain Resistance

5: Removed after 5 minutes (hot water running)
 4: Removed by manual cleaning (weak detergent)
 3: Removed by mechanical cleaning (strong detergent)
 2: Removed by immersion (24 hrs in suitable solvent)
 1: Stain not removed

ASTM C1378-04
UNI EN ISO 10545.14 **5**

Water Absorption

ASTM C-373
UNI EN ISO 10545.3 **<0.5**

Absorbs 0-.5% Absorbs .5-3% Absorbs 3-7% Absorbs 7% +

Impervious Interior/exterior Frost Resistant
Vitreous Interior/exterior Frost Resistant
Semi-Vitreous Indoor use only
Non-Vitreous Indoor use only

Breaking Strength

Industry standard should be greater than 250 lbs or 50 N/MM2

ASTM C648
UNI EN ISO 10545.4 **≥35**

Facial Dimension

ASTM c499-09
UNI EN ISO 10545.02

	Standard	Tolerance	Result
flatness	± 5mm	± .5%	
thickness	± 6mm	± .5%	
straightness	± 4.5mm	± .5%	
squareness	± 5.4mm	± .6%	
sides L/W	± 1.1mm / ± 4.5mm	± .5%	

Chemical Resistance

ASTM C650
UNI EN ISO 10545.13

Allowances for:

acid
 bases
 chemicals

Leed Information

REQUIREMENTS FOR COMMERCIAL INTERIORS/NEW CONSTRUCTION

Sustainable Sites	Allowances for:	Materials & Resources	1 Point	2 Points
Site selection SS CREDIT 1 Heat Island Effect-non roof Material with a solar reflectant index of at least 29.	1 Point	M&R CREDIT 2 Construction Waste Management: Recycling salvaged construction waste in to new reusable materials.	50% <input type="checkbox"/>	70% <input type="checkbox"/>
Energy & Atmosphere EA CREDIT 4 Green Power: Products that optimize energy performance for floors and walls using thermal conductivity. BTU-FT	1 Point	M&R CREDIT 4.1-4.2 Recycled Content: The sum of post consumer plus 1/2 of the pre consumer reps at least 10-20% of total value of materials.	10% <input type="checkbox"/>	20% <input type="checkbox"/>
Indoor Environmental Quality Low-Emitting Materials-Flooring Systems IEQ CREDIT 3.1-7 Green Cleaning: Reducing occupants exposure to hazardous cleaning chemicals.	1 Point	M&R CREDIT 5 Regional Materials: Materials manufactured within 500 miles of the project site.	10% <input type="checkbox"/>	20% <input type="checkbox"/>
IEQ CREDIT 4.1 Low Emitting Adhesives: Products less than 65 G/L VOC	<input type="checkbox"/>	Innovation in Design ID CREDIT 1 Innovation in Design Measurable exemplary environmental performance.	1-5 Points <input type="checkbox"/>	
IEQ CREDIT 4.3 Low Emitting Materials: Flooring systems.	<input type="checkbox"/>			

Type: **Porcelain Stoneware**

Product Line: **Royal Stone**

The marketing name for this product is property of Cancos Tile Corp. This same product may be marketed under different names.